

Carthage Crushed Limestone

1331 Civil War Road
PO Box 1086
Carthage, MO 64836

Phone: 417-358-3257
Fax: 417-358-5527

Description

Ground, screened and air classified granular and powder grades produced from high calcium calcitic limestone quarried from underground mines. "Calcite, "crushed marble", "ground limestone" are synonymous with ground natural "calcium carbonate".

Screen Analysis (Typical) slight variations due to segregations etc...

Cumulative % Thru US Screening	C-4
3 Mesh (1/4")	
4 Mesh (3/16")	
6 Mesh (1/8")	
8 Mesh (3/32")	
12 Mesh (1/16")	
16 Mesh (3/64")	
20 Mesh (1/32")	
40 Mesh (.016")	99.8
60 Mesh (.010")	99
100 Mesh (.006")	90
200 Mesh (.003")	62
325 Mesh (.002")	50

Average Bulk Density (lbs/ft)	85
--------------------------------------	----

Color	Off white, light gray tint
Alkalinity (as NaOH)	0.2 mg / g
pH	9.3 (saturated solution)
Hardness	3 Moh, non-abrasive
Solubility	0.0035 gm / 100 ml H ₂ O @ 100° C
Particle Shape	Irregular, uniaxial
Specific Gravity	2.71 g / cm ³
Refractive Index	1.6
Weight / Solid Gallon	22.6 lbs / solid gallon (0.0443 solid gallon / lb.)
Linear Expansion Coefficient	4.3 x 10 / C
Moisture	0.10%

Chemical Analysis (Typical)

Calcium Carbonate (CaCO ₃)	95%	Iron Oxide (Fe ₂ O ₃)	0.15%
Magnesium Carbonate (MgCO ₃)	0.80%	Manganese Oxide (MnO)	0.04%
Silica and Silicates (SiO ₂)	less than 3%	Copper Oxide (CuO)	2 ppm
Aluminum Oxide (Al ₂ O ₃)	0.15%	Lead (Pb & Hg)	less than 3ppm
Cadmium	less than 1ppm	Arsenic	less than 2ppm

Disclaimer

The recommendations, suggestions, descriptions, possible uses, specifications, material safety data, analysis, and other information regarding the product of products on this web page (the "Information") is to the best of our knowledge, true and accurate, but the information is without guarantee or warranty, and all liability is disclaimed. The data or information is also made pursuant to the terms of the [GENERAL COMPANY DISCLAIMER STATEMENT](#).